

## VG 10

ANALYSIS	LIMIT	TEST METHOD
Absolute Viscosity at 60°C,Poises	Min. 800	IS 1206 (Part 2)
Kinematic Viscosity at 135°C,cst	Min. 250	IS 1206 (Part 3)
Flash Point (Cleveland Open Cup),°C	Min. 220	IS 1209
Solubility in Trichloroethylene,%	Min. 99	IS 1206
Softening Point (R&B) ,°C	Min. 40	IS 1205
Penetration@25°C ,0.1 mm 100 gm,5 Sec.	80-100	IS 1203
<b>Test on Residue from thin film oven tests /RTFOT</b>		
Viscosity Ratio at 60°C	Max. 4.0	IS 1206 (Part 2)
Ductility at 25°C,Cm,after thin film over test	Min. 75	IS 1208
Specific Gravity@27/27°C	Min. 0.99	IS 1202